

DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

"We Test Per Your Request"

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

July 13, 2018

Burch
4200 Brockton Dr SE
Grand Rapids, MI 49512

Reference: Laboratory Test Report
Lab Identification No. 31384
Invoice No. 62512

Dear Burch:

One (1) fabric sample, identified as **STYLE: POSY** was received and tested in accordance with the California Technical Bulletin 117-2013, Section 1, Cover Fabric Test. The results are as follows:

Test Results
Vertical Char Lengths

9mm

10mm

9mm

The sample submitted **meets** the requirements of the above standard. There were no ignitions or smoldering after 45 minutes on any of the three specimens tested. In addition, none of the three test specimens displayed a char which was greater than 45 mm.


If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Brian S. Dement

BSD/mr





DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

"We Test Per Your Request"

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

July 13, 2018

Burch
4200 Brockton Dr SE
Grand Rapids, MI 49512

Reference: Laboratory Test Report
Lab Identification No. 31384
Invoice No. 62512

Dear Burch:

One (1) fabric sample, identified as **STYLE: POSY**, was received and tested in accordance with the UPHOLSTERED FURNITURE ACTION COUNCIL Fabric Classification Test Method--1990. The results are as follows:

Test Results

Vertical Char Lengths

9mm 8mm 11mm

Class

I


If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Brian S. Dement

BSD/mr





DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

"We Test Per Your Request"

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

July 13, 2018

Burch
4200 Brockton Dr SE
Grand Rapids, MI 49512

Reference: Laboratory Test Report
Lab Identification No. 31384
Invoice No. 62512

Dear Burch:

One (1) fabric sample, identified as **STYLE: POSY** was received and tested in accordance with the NFPA 260, "Cigarette Ignition Resistance of Components of Upholstered Furniture, 2013 Edition", (Cover Fabric Test). The results are as follows:

Test Results

Vertical Char Lengths

9mm 8mm 11mm

The sample submitted **meets** the requirements of the above standard and may be considered a **Class I Cover Fabric**. There were no ignitions on any of the three specimens tested. In addition, none of the three test specimens displayed a vertical char which was equal to or greater than 45 mm.

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Brian S. Dement

BSD/mr

