

DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

"We Test Per Your Request"

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

November 8, 2024

Burch Fabrics
4200 Brockton Dr SE
Grand Rapids, 49512

Reference: Laboratory Test Report
Lab Identification No. 62097
Invoice No. 93406

Dear Burch Fabrics,

One (1) sample, identified as **Preston**, was received and tested in accordance with the California Technical Bulletin 117-2013, Section 1, Cover Fabric Test. The results are as follows:

Test Results

<u>Vertical Char Lengths</u>		
8mm	8mm	8mm


The sample submitted **meets** the requirements of the above standard. There were no ignitions or smoldering after 45 minutes on any of the three specimens tested. In addition, none of the three test specimens displayed a char which was greater than 45 mm.

Sincerely,

Brian S. Dement

BSD/mr





DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

"We Test Per Your Request"

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

November 8, 2024

Burch Fabrics
4200 Brockton Dr SE
Grand Rapids, 49512

Reference: Laboratory Test Report
Lab Identification No. 62097
Invoice No. 93406

Dear Burch Fabrics,

One (1) sample, identified as **Preston**, was received and tested in accordance with the NFPA 260, "Cigarette Ignition Resistance of Components of Upholstered Furniture, 2024 Edition", (Cover Fabric Test). The results are as follows:

Test Results

Vertical Char Lengths

8mm

8mm

8mm

*Date Tested: November 7, 2024

*Conditioned minimum of 4 hours @ 70±5°F and >65% RH


The sample submitted **meets** the requirements of the above standard and may be considered a **Class I Cover Fabric**. There were no ignitions on any of the three specimens tested. In addition, none of the three test specimens displayed a vertical char which was equal to or greater than 45 mm.

Sincerely,

Brian S. Dement

BSD/mr





DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

"We Test Per Your Request"

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

November 8, 2024

Burch Fabrics
4200 Brockton Dr SE
Grand Rapids, 49512

Reference: Laboratory Test Report
Lab Identification No. 62097
Invoice No. 93406

Dear Burch Fabrics,

One (1) sample, identified as **Preston**, was received and tested in accordance with the UPHOLSTERED FURNITURE ACTION COUNCIL Fabric Classification Test Method--1990. The results are as follows:

Test Results

<u>Vertical Char Lengths</u>		
8mm	9mm	8mm

The sample submitted **meets** the requirements of the above standard and is a **Class I Cover Fabric**. There were no ignitions on any of the three specimens tested. In addition, none of the three test specimens displayed a vertical char which was equal to or greater than 44 mm.

Sincerely,

Brian S. Dement

BSD/mr

