ISO: 9001 Certified

TB Cal. 117-2013 Quality Assurance Lab Test Report

Date:

10/30/2018

Material #:

Material Name:

Principle

Reference Material:

Contents:

35.84% OLEFIN, 29.42% PIRPOLY, 18.89% POLY 15.85% PCRPOLY

Wgt oz/Linear yd:

16.896

Section 1: Cover Fabric Test

Length of Char in Inches

Specimen #1

0.750 Inch

Specimen #2

0.750 Inch

Specimen #3

0.750 Inch

Char Length:

Pass

If the char measures 1.8 inches or less, the result is passing. If the char measures more than 1.8 inches, the result is failing.

45 Minute Smolder Resistance:

Pass

QA Lab Manager:

Barbara Grant

Date:

10/30/2018

Telephone #:

828-893-4382

ISO: 9001 Certified

NFPA 260 Certificate Quality Assurance Lab Test Report

Date:

10/30/2018

Material #:

Material Name:

Principle

Reference Material:

Contents:

35.84% OLEFIN, 29.42% PIRPOLY, 18.89% POLY 15.85% PCRPOLY

Wgt oz/Linear yd:

16.896

Section 1: Cover Fabric Test

Length of Char in Inches

Specimen #1 0.750 Inch Specimen #2 0.750 Inch Specimen #3 0.750 Inch Char Length: Class I

If the char measures 1.75 inches or less, passing results are categorizeed as Class I. If the char measures more than 1.75 inches, the result is failing, Failing results are categorized as Class II

QA Lab Manager: Barbara Grant

Date: 10/30/2018

Telephone #: 828-893-4382 ISO: 9001 Certified

UFAC Quality Assurance Lab Test Report

Date:

10/30/2018

Material #:

Material Name:

Principle

Reference Material:

Contents:

35.84% OLEFIN, 29.42% PIRPOLY, 18.89% POLY 15.85% PCRPOLY

Wgt oz/Linear yd:

16.896

Section 1: Cover Fabric Test

Length of Char in Inches

Specimen #1 0.750 Inch Specimen #2

0.750 Inch Specimen #3 0.750 Inch

Char Length: Class I

If the char measures 1.75 inches or less, passing results are categorizeed as Class I. If the char measures more than 1.75 inches, the result is failing, Failing results are categorized as Class II

QA Lab Manager: Barbara Grant

Date: 10/30/2018

Telephone #: 828-893-4382