

TB Cal. 117-2013
Quality Assurance Lab Test Report

Date:	4/11/2014
Material #:	Profile
Sales Order:	Needle 5 Back7
Contents:	100% Polyester
Weight oz/Linear yd:	14.592

Section 1: Cover Fabric Test

Length of char in inches

Specimen # 1	0.25
Specimen # 2	0.313
Specimen # 3	0.50

Char Length: Pass (X) Fail ()

If the char measures 1.8 inches or less, the result is passing.

If the char measures more than 1.8 inches, the result is failing

45 Minute Smolder Resistance: Pass (X) Fail ()

QA Lab Manager:	Barbara Grant
Date:	04/11/2014
Telephone #	828-893-4382

NFPA 260 Certificate - 2009
Quality Assurance Lab Test Report

Date DELIVERED APR 14 2014

Customer Burch Fabrics

Pattern F-0217267-01 Profile

Length of char in inches

Specimen # 1 .075

Specimen # 2 .075 Class 1

Specimen # 3 .055

If the char measures 1.75 inches or less, the result is passing. Passing results are categorized as Class 1.

If the char measures more than 1.75 inches, the result is failing. Failing results are categorized as Class 2.

Rexie Mitchell

QA Lab Manager

DELIVERED APR 14 2014

Date

UFAC
Quality Assurance Lab Test Report

Date DELIVERED APR 14 2014

Customer Burch Fabrics

Pattern F-0217267-01 (Profile)

Length of char in inches

Specimen # 1 0.25 Class 1

Specimen # 2 0.30

Specimen # 3 0.50

If the char measures 1.75 inches or less, the result is passing. Passing results are categorized as Class 1.

If the char measures more than 1.75 inches, the result is failing. Failing results are categorized as Class 2.

Renée Mitchell

QA Lab Manager

DELIVERED APR 14 2014

Date