



DIVERSIFIED

TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

"We Test Per Your Request"

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

April 9, 2014

Burch
4200 Brockton Dr SE
Grand Rapids, MI 49512

Reference: Laboratory Test Report
Lab Identification No. 9904
Invoice 40649 (Attached)

Dear Ms. Turner:

One (1) fabric sample, identified as **RIDDLE**,
was received and tested in accordance with the California
Technical Bulletin 117-2013, Section 1, Cover Fabric Test.
The results are as follows:

Test Results - Char

11mm	15mm	16mm
------	------	------

The sample submitted **meets** the requirements of the above
standard. There were no ignitions or smoldering after 45
minutes on any of the three specimens tested. In addition,
none of the three test specimens displayed a char which was
greater than 45 mm.

If there are any questions or when we can be of further
assistance, please let us know.

Sincerely,

Bobby E. Puett

BEP/mr
Attachment

Received: 04/10/2014 Completed: 04/10/2014 Letter: U1 JE P.O.#: AN00219074 Test Report #: 3-01600-1-RV

**Client's
Identification**

Riddle

Tested For: Burch
4200 Brockton Dr SE
Grand Rapids, MI 49512

Key Test: UFAC Fabric RVNC

PC.4H

TEST PERFORMED: UFAC Fabric Classification Test Method 1990
Cigarette Ignition Resistance of Fabric Intended for Use in Upholstered Furniture

RESULTS:			RETEST (If Required)	
Specimen #	TEST (yes/no/SE)	Char Length on Vertical Panel (inches)	Ignition (yes/no/SE)	Char Length on Vertical Panel (inches)
1	No	0.9		
2	No	0.7		
3	No	0.6		

ABBREVIATION WHICH MAY BE USED:

SE = Indicates that the cigarette self-extinguished prior to burning its entire length. When this occurs, a "retest" of that specimen is performed.

EC = Escalating combustion. Specimen extinguished by technician. No char length measurement taken.

CLASSIFICATION SYSTEM:

Class I - For each specimen: No obvious ignition; char length less than 1.75".
(Indicates propensity to resist cigarette ignition in conjunction with standard foam filling material.)

Class II - For any specimen: Obvious ignition or char length 1.75" or greater.
(Indicates inability to resist cigarette ignition in conjunction with standard foam filling material.)

RETEST PROVISION:

Applies only to cigarettes that self-extinguish. It does not apply to specimens which ignite or have a char length of 1.75" or greater.

CONCLUSION: Based on the above Results and Criteria, the item tested is assigned a:

☒ Class I rating; ☐ Class II rating



The
Govmark
Organization, Inc.

96-D Allen Boulevard
Farmingdale, New York 11735-5626 USA
Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956
e-mail: info@govmark.com

Page 2

Received: 04/10/2014	Completed: 04/10/2014	Letter: U1	JE	P.O.#: AN00219074	Test Report #: 3-01600-1-RV
----------------------	-----------------------	------------	----	-------------------	-----------------------------

Client's Identification	Riddle
----------------------------	--------

Tested For: Burch
4200 Brockton Dr SE
Grand Rapids, MI 49512

Key Test: UFAC Fabric RVNC

REMARKS: None.

COMMENTARY: The cigarette ignition source used in this test conforms to the physical parameters set forth in the test standard. The actual propensity of the cigarette (that is currently manufactured) to cause ignition of materials under test might be different than the cigarette that was manufactured at the inception of the test standard.

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified by UFAC Fabric Classification Test Method 1990.



AUTHORIZED SIGNATURE

THE GOVMARK ORGANIZATION, INC. /pm

APR 23 2014

RV.04.23.14 /tm

MS. PHYLLIS PETTIT

(Page 2 of 2)