

# Burch

ISO: 9001 Certified

## ***TB Cal. 117-2013 Quality Assurance Lab Test Report***

**Test Date:** 09/23/2022  
**Material #:**  
**Material Name:**  
**Customer ID:** Rivulet Crypton  
**Reference Material:**  
**Contents:** 82.22% PCRPOLY, 17.78% NYLON  
**Wgt oz/Linear yd:** 15.344

### ***Section 1: Cover Fabric Test***

---

#### **Length of Char in Inches**

**Specimen #1** 0.438 Inch  
**Specimen #2** 0.375 Inch  
**Specimen #3** 0.438 Inch  
**Char Length:** Pass

If the char measures 1.8 inches or less, the result is passing.  
If the char measures more than 1.8 inches, the result is failing.

**45 Minute Smolder  
Resistance:** Pass

|                        |                      |
|------------------------|----------------------|
| <b>QA Lab Manager:</b> | <b>Barbara Grant</b> |
| <b>Date:</b>           | <b>10/03/2022</b>    |
| <b>Telephone #:</b>    | <b>828-893-4382</b>  |

# Burch

ISO: 9001 Certified

## ***NFPA 260 Certificate Quality Assurance Lab Test Report***

Test Date: 09/23/2022  
Material #:  
Material Name:  
Customer ID: Rivulet Crypton  
Reference Material:  
Contents: 82.22% PCRPOLY, 17.78% NYLON  
Wgt oz/Linear yd: 15.344

### ***Section 1: Cover Fabric Test***

---

|              | Length of Char in Inches |
|--------------|--------------------------|
| Specimen #1  | 0.438 Inch               |
| Specimen #2  | 0.375 Inch               |
| Specimen #3  | 0.438 Inch               |
| Char Length: | Class I                  |

If the char measures 1.75 inches or less, passing results are categorized as Class I. If the char measures more than 1.75 inches, the result is failing, Failing results are categorized as Class II

|                 |               |
|-----------------|---------------|
| QA Lab Manager: | Barbara Grant |
| Date:           | 10/03/2022    |
| Telephone #:    | 828-893-4382  |

# Burch

ISO: 9001 Certified

## UFAC

### Quality Assurance Lab Test Report

Test Date: 09/23/2022  
Material #:  
Material Name:  
Customer ID: Rivulet Crypton  
Reference Material:  
Contents: 82.22% PCRPOLY, 17.78% NYLON  
Wgt oz/Linear yd: 15.344

#### Section 1: Cover Fabric Test

---

##### Length of Char in Inches

Specimen #1 0.438 Inch  
Specimen #2 0.375 Inch  
Specimen #3 0.438 Inch  
Char Length: Class I

If the char measures 1.75 inches or less, passing results are categorized as Class I. If the char measures more than 1.75 inches, the result is failing, Failing results are categorized as Class II

|                 |               |
|-----------------|---------------|
| QA Lab Manager: | Barbara Grant |
| Date:           | 10/03/2022    |
| Telephone #:    | 828-893-4382  |