

ISO: 9001 Certified

TB Cal. 117-2013
Quality Assurance Lab Test Report

Date: 12/06/2017
Material #:
Material Name: Rush Hour
Reference Material:
Contents: 100.00% POLY
Wgt oz/Linear yd: 15.392

Section 1: Cover Fabric Test

	Length of Char in Inches
Specimen #1	0.250 Inch
Specimen #2	0.250 Inch
Specimen #3	0.250 Inch
Char Length:	Pass

If the char measures 1.8 inches or less, the result is passing.
If the char measures more than 1.8 inches, the result is failing.

45 Minute Smolder
Resistance: Pass

QA Lab Manager:	Barbara Grant
Date:	12/06/2017
Telephone #:	828-893-4382

ISO: 9001 Certified

***NFPA 260 Certificate
Quality Assurance Lab Test Report***

Date: 12/06/2017
Material #:
Material Name: Rush Hour
Reference Material:
Contents: 100.00% POLY
Wgt oz/Linear yd: 15.392

Section 1: Cover Fabric Test

	Length of Char in Inches
Specimen #1	0.250 Inch
Specimen #2	0.250 Inch
Specimen #3	0.250 Inch
Char Length:	Class I

If the char measures 1.75 inches or less, passing results are categorized as Class I. If the char measures more than 1.75 inches, the result is failing, Failing results are categorized as Class II

QA Lab Manager:	Barbara Grant
Date:	12/06/2017
Telephone #:	828-893-4382

ISO: 9001 Certified

UFAC
Quality Assurance Lab Test Report

Date: 12/06/2017
Material #:
Material Name: Rush Hour
Reference Material:
Contents: 100.00% POLY
Wgt oz/Linear yd: 15.392

Section 1: Cover Fabric Test

	Length of Char in Inches
Specimen #1	0.250 Inch
Specimen #2	0.250 Inch
Specimen #3	0.250 Inch
Char Length:	Class I

If the char measures 1.75 inches or less, passing results are categorized as Class I. If the char measures more than 1.75 inches, the result is failing, Failing results are categorized as Class II

QA Lab Manager:	Barbara Grant
Date:	12/06/2017
Telephone #:	828-893-4382