

# CAL 117 Section E, Part I – Upholstery Fabrics

RECEIVED DEC 3 1 2013

Date \_\_\_\_\_

Customer Burch Fabrics

Pattern Summit

Warp	1	2	3	4	5
Flame Spread with Nap (seconds)					
Flame Spread without Nap (seconds)	DNI	DNI	DNI	DNI	DNI

Fill	1	2	3	4	5
Flame Spread with Nap (seconds)					
Flame Spread without Nap (seconds)	DNI	DNI	DNI	DNI	DNI

DNI - (Did Not Ignite)

Requirements:

With Nap – Minimum flame spread of any individual specimens shall not be less than 7 seconds.

Without Nap – Minimum flame spread of any individual specimens shall not be less than 3.5 seconds.

Conclusion:

The above results indicate Class 1 with the stated requirements.

I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified by California Technical Bulletin 117, Section E, part I Upholstered Fabrics dated January 1980.

Renee Mitchell  
QA Lab Manager

RECEIVED DEC 3 1 2013

\_\_\_\_\_  
Date

**NFPA 260 Certificate - 2009**  
**Quality Assurance Lab Test Report**

**Date** RECEIVED DEC 3 1 2013

**Customer** Burch Fabrics

**Pattern** Summit

**Length of char in inches**

**Specimen # 1** DNI class 1

**Specimen # 2** DNI

**Specimen # 3** DNI

*DNI - (did not ignite)*

If the char measures 1.75 inches or less, the result is passing. Passing results are categorized as Class 1.

If the char measures more than 1.75 inches, the result is failing. Failing results are categorized as Class 2.

Renee Mitchell  
QA Lab Manager

RECEIVED DEC 3 1 2013  
Date

**UFAC**  
**Quality Assurance Lab Test Report**

Date RECEIVED DEC 3 1 2013

Customer Burch Fabrics

Pattern Summit

Length of char in inches

Specimen # 1 DNI class 1

Specimen # 2 DNI

Specimen # 3 DNI

DNI - (Did not Ignite).

If the char measures 1.75 inches or less, the result is passing. Passing results are categorized as Class 1.

If the char measures more than 1.75 inches, the result is failing. Failing results are categorized as Class 2.

Renee Mitchell  
QA Lab Manager

RECEIVED DEC 3 1 2013  
Date