

DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

"We Test Per Your Request"

April 7, 2015



BURCH
FABRICS

Reference: Laboratory Test Report
Lab Identification No. 14581
Invoice No. 45343 (Attached)

Dear Ms. Houser:

One (1) fabric sample, identified as **TAGLINE** was received and tested in accordance with the California Technical Bulletin 117-2013, Section 1, Cover Fabric Test. The results are as follows:

Test Results - Char

15mm 15mm 14mm


The sample submitted **meets** the requirements of the above standard. There were no ignitions or smoldering after 45 minutes on any of the three specimens tested. In addition, none of the three test specimens displayed a char which was greater than 45 mm.

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Brian S. Dement

BSD/mr
Attachment



DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

"We Test Per Your Request"

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

February 9, 2016



Reference: Laboratory Test Report
Lab Identification No. 18478
Invoice No. 49355 (Attached)

Dear Ms. Houser:

One (1) fabric sample, identified as **TAGLINE** was received and tested in accordance with the NFPA 260, "Cigarette Ignition Resistance of Components of Upholstered Furniture, 2009 Edition", (Cover Fabric Test). The results are as follows:

<u>Test Results</u>		
<u>Vertical Char Lengths</u>		
8mm	9mm	9mm


The fabric sample submitted meets the requirements of the above standard and may be considered a Class I Cover Fabric. There were no ignitions on any of the three specimens tested. In addition, none of the three test specimens displayed a vertical char which was equal to or greater than 45 mm.

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Bobby E. Puett

BEP/mr
Attachment



DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

"We Test Per Your Request"

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

February 9, 2016



BURCH
FABRICS

Reference: Laboratory Test Report
Lab Identification No. 18478
Invoice No. 49355 (Attached)

Dear Ms. Houser:

One (1) fabric sample, identified as **TAGLINE** was received and tested in accordance with the UPHOLSTERED FURNITURE ACTION COUNCIL Fabric Classification Test Method--1990. The results are as follows:

Test Results
Vertical Char Lengths

8mm 9mm 9mm

Class

I

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Bobby E. Puett

BEP/mr
Attachment