



TB Cal. 117-2013
Quality Assurance Lab Test Report

| | |
|-----------------------------|-----------------|
| Date: | 4/11/2014 |
| Material #: | Theory |
| Sales Order: | Needle 7 Back 8 |
| Contents: | 100% Polyester |
| Weight oz/Linear yd: | 13.728 |

Section 1: Cover Fabric Test

Length of char in inches

| | |
|---------------------|------|
| Specimen # 1 | 0.25 |
| Specimen # 2 | 0.50 |
| Specimen # 3 | 0.50 |

Char Length: Pass (X) Fail ()

If the char measures 1.8 inches or less, the result is passing.

If the char measures more than 1.8 inches, the result is failing

45 Minute Smolder Resistance: Pass (X) Fail ()

| | |
|------------------------|---------------|
| QA Lab Manager: | Barbara Grant |
| Date: | 04/11/2014 |
| Telephone # | 828-893-4382 |



NFPA 260 Certificate - 2009
Quality Assurance Lab Test Report

DELIVERED APR 14 2014

Date _____

Customer Burch Fabrics

Pattern F-0216569-01 Theory

Length of char in inches

Specimen # 1 0.50 class 1

Specimen # 2 0.50

Specimen # 3 0.50

If the char measures 1.75 inches or less, the result is passing. Passing results are categorized as Class 1.

If the char measures more than 1.75 inches, the result is failing. Failing results are categorized as Class 2.

Renee Mitchell
QA Lab Manager

DELIVERED APR 14 2014

Date



UFAC
Quality Assurance Lab Test Report

Date DELIVERED APR 14 2014

Customer Burch Fabrics

Pattern F-0216569-01 Theory

Length of char in inches

Specimen # 1 .025 Class 1

Specimen # 2 .035

Specimen # 3 .035

If the char measures 1.75 inches or less, the result is passing. Passing results are categorized as Class 1.

If the char measures more than 1.75 inches, the result is failing. Failing results are categorized as Class 2.

Roxie Mitchell

QA Lab Manager

DELIVERED APR 14 2014

Date